

COR+GARD® CHEMICAL RESISTANCE

AGENT	% WEIGHT INCREASE (DECREASE)
Methylated Spirits	0.514
Distilled Water	0.09
10% Aq. Sulfuric Acid (H ₂ SO ₄)	0.136
70% Aq. Sulfuric Acid (H ₂ SO ₄)	4.10
Gasoline - 90 Octane	0.01
30 wt. SAE Motor Oil	0.02
Isopropyl Alcohol	0.11
Salt Water - 5%	0.10
20% Nitric Acid (HNO ₃)	2.7
10% Sodium Hydroxide (NaOH)	0.086
50% Sodium Hydroxide (NaOH)	0.12
Methyl Ethyl Ketone	D
Xylene	D
10% Acetic Acid (HOAc)	6.14
10% Hydrochloric Acid (HCl)	1.4
30% Hydrochloric Acid (HCl)	0.088
20% Ammonium Hydroxide (NH ₄ OH)	0.84
10% Ammonium Hydroxide (NH ₄ OH)	0.81
95% Ethyl Alcohol	0.37
Acetone	2.1
Ethylene Dichloride	1.5
Toluene	1.4
JP-4 Fuel	(0.01)
10% Citric Acid	0.80
40% Chromic Acid	(5.82)

Chemical & Solvent Resistance ASTM D543 60T 3" X 1" X0.125"